

SC2001 – Heat Cure

Silicone Resin

DESCRIPTION

SC2001 is a two-part, general purpose potting and encapsulating compound designed for the protection for electronic devices. It has exceptional high temperature properties, suitable for use in applications where the operating temperature will be up to 200 °C. The preferred cure schedule for **SC2001** is 3 hours at 80 °C.

READ ENTIRE TECHNICAL BULLETIN BEFORE USING THIS PRODUCT

FEATURES AND BENEFITS

- Exceptionally wide temperature range; ideal for applications reaching very high temperatures
- Simple 1:1 mix ratio; aids ease of processing
- Excellent flexibility; does not stress delicate components
- Meets UL94 V-0 approval; high level of flame retardancy

APPROVALS

Standard	Status
RoHS Compliant (2015/863/EU)	Yes
UL Approval	Meets UL94 V-0

PRODUCT INFORMATION

For available packaging sizes please visit:

electrolube.com

PHYSICAL PROPERTIES


Category	Results
Liquid Properties	
Base Material	Silicone
Appearance Part A Part B	Black Liquid White Liquid
Density Part A - (g/mL) Part B - (g/mL)	1.4 1.4
Viscosity (mPa s 23 °C) Part A Part B Mixed System	4000 3000 3500
Mix Ratio Weight Volume	1:1 1:1
Usable Life (20 °C)	30 minutes
Cure Time (80 °C)	3 hour
Storage Conditions	Above 15 °C, Below 30 °C
Shelf Life	12 Months
Cured System	
Color (Mixed System)	Dark Grey
Thermal Conductivity (W/m.K)	0.6
Cured Density (g/mL)	1.4
Temperature Range (°C)	-50 to 200
Max Temperature Range (Short Term (°C)/30 Mins) (Application and Geometry Dependent)	+225
Dielectric Strength (kV/mm)	20

Category	Results
Shore Hardness	A50
Flame Retardancy	Yes, Meets UL94 V-0
Loss Tangent @ 50 Hz	0.0016
Permittivity @ 50 Hz	3
Dielectric Constant @ 100 Hz	3.1
Dissipation Factor @ 100 Hz	0.0027

APPLICATION GUIDELINES – RESIN PACKS

Mixing Procedures

When in Resin pack form, the resin and hardener are mixed by removing the clip and moving the contents around inside the pack until thoroughly mixed. To remove the clip, remove both end caps, grip each end of the pack, and pull apart gently. By using the removed clip, take special care to push unmixed material from the corners of the pack. Mixing normally takes from three to four minutes depending on the skill of the operator and the size of the pack. Both the resin and hardener are evacuated prior to packing so the system is ready for use immediately after mixing. The corner may be cut from the pack so that it may be used as a simple dispenser. There is also a YouTube video ([Mixing Instructions](#)) available on the Electrolube channel to show the mixing process.



APPLICATION GUIDELINES - BULK

Bulk Mixing

When mixing, care must be taken to avoid the introduction of excessive amounts of air. Automatic mixing equipment is available which will not only mix both the resin and hardener accurately in the correct ratio but do this without introducing air. Containers of Part A (Resin) and Part B (Hardener) should be kept sealed at all times when not in use to prevent the ingress of moisture. Bulk material must be thoroughly mixed before use. Incomplete mixing or use of the wrong mix ratio will result in erratic or partial curing.

GENERAL

Sedimentation of the resin has been minimised by careful attention to the formulation. However, any sediment which may have occurred over long periods of time must be dispersed before removing any material from the container. This dispersion can be carried out (if necessary) by stirring with a broad bladed spatula or gently rolling the can. Take care not to introduce excessive amounts of air during this operation or it may be necessary to re-evacuate the resin. Sedimentation will be accelerated by storage at high temperatures. Sedimentation found in resin packs forms no problem since the sediment is re-mixed when the pack is used.

ADDITIONAL INFORMATION

Cleaning: It is far easier for machines & containers to be cleaned before the resin has been allowed to cure. RRS is suitable for cleaning machines and containers and cured resin may be slowly softened and removed by soaking in our RRS.

All surfaces must be clean before resin is applied. Certain materials, chemicals, curing agents and plasticizers can inhibit the cure of silicone encapsulants. Most notable of these include:

- Organotin and other organometallic compounds
- Silicone rubber containing organotin catalyst
- Sulphur, polysulphides, polysulphones or other sulphur containing materials
- Amines, urethanes, or amine-containing materials
- Unsaturated hydrocarbon plasticisers
- Some solder flux residues

Curing: SC2001 can easily become contaminated by resins of other chemistry types/certain chemical reagents (in particular: amines, peroxides, transition metal catalysts). It is advised that when curing SC2001 in an oven that no other chemical based products are present. If an epoxy resin has been present in the curing oven, then it is recommended that the oven is ventilated for 10 to 15 minutes prior to curing SC2001.

Storage: When storing under very cold conditions, the hardener may crystallise. If this occurs, simply warm (40 °C) the container gently until all crystals have re-melted.

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

To confirm this document is the most recent version, please contact

TechnicalSupportTeam@hkw.co.uk

www.electrolube.com

North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460	Europe Ashby Park Coalfield Way Ashby de la Zouch Leicestershire, LE65 1JR, UK 44.01530.41960	Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100
--	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.