

# ALPHA® HiTech AD13-9692B

**Low Temperature** 

### **DESCRIPTION**

**ALPHA HiTech AD13-9692B** is a one component epoxy used to cure in low-temperature ranges. It is designed for bonding heat sensitive devices. It provides the user with a balanced set of the following features and benefits:

- Fast cure at low-temperature
- Excellent adhesion
- Excellent workability
- Halogen-free

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

## **APPLICATION GUIDELINES**

Storage	Thawing	Application	Curing
<ol> <li>Store at below         <ul> <li>20 °C to guarantee product stability.</li> </ul> </li> <li>Upright Position, tip facing the bottom</li> </ol>	<ol> <li>Remove the syringe from the freezer.</li> <li>Set aside at room temperature for 2 hours.</li> <li>Do not open the cap before the product is sufficiently thawed.</li> <li>Product should not be refrozen after thawed.</li> <li>To prevent contamination of unused product, do not return any material to its original container.</li> </ol>	ALPHA HiTech AD13-9692B is designed for bonding heat sensitive devices, which requires low temperature curing process.	For full property development, cure at 80 °C and hold for a minimum of 30minutes (Convection oven).





# **TECHNICAL DATA**

Category	Results		
Typical Uncured Material Properties			
Product Name	AD13-9692B		
Chemistry	Ероху		
Appearance	Black paste		
Viscosity (Malcom PC-10A, 30rpm @25 °C, cps)	8,000 to 18,000		
Specific Gravity	1.1 to 1.3		
Thixotropic Index	4.3 to 5.3		
Pot Life @ 25 °C, days	3		
Shelf Life at ≤-20 °C, months	6		
Available Packaging	10cc, 30cc syringes		
Typical Cured Material Properties			
Glass Transition (Tg), °C via TMA	45 ± 5		
CTE (α <sub>1</sub> ), <tg, ppm="" td="" tma<="" via=""><td>55 ± 5</td></tg,>	55 ± 5		
CTE (α <sub>2</sub> ), >Tg, ppm via TMA	175 ± 10		
Corrosion, 95-hr @40 °C, 95%RH	None		
Moisture Absorption, 24-hr @H <sub>2</sub> O/25 °C, wt%	≤ 1.0		
Insulation Resistance, 96-hr@40 °C, 95%RH	≥1 X 10 <sup>12</sup>		
Hardness (Shore D)	65 to 75		







#### **SAFETY & WARNING**

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at MacdermidAlpha.com/assembly-solutions/knowledge-base.** 

### **CONTACT INFORMATION**

## To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

www.macdermidalpha.com

## North America

109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460

#### **Europe**

Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400

#### Asia

8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY (SI MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indicent, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.



Issue: 20 July 2023