

ALPHA[®] FLS0016T-5D

No Rosin, Low Solid, High Reliability Flux

DESCRIPTION

ALPHA FLS0016T-5D is a no rosin, low solid and high reliability flux. After wave soldering, **ALPHA FLS0016T-5D** leaves only a low level of flux residues which reduces interference with pin testing and results to excellent board cosmetics.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

APPLICATION GUIDELINES

Flux Application: ALPHA FLS0016T-5D is suggested to be applied by foam or spray application. A proper preheat setting will help to achieve a goal of best soldering performance. Please refer below recommend preheat setting:

Operating Parameter	Recommendation
Flux application	Foam, Spray
Top-Side Preheat Temperature (Direct Wave Soldering)	Range: 70 to 100 °C
Bottom side Preheat Temperature (Direct Wave Soldering)	Range: 80 to 140 °C
Top-Side Preheat Temperature Above Aperture Opening (Selective Soldering)	Range: 50 to 100 °C
Bottom side Preheat Temperature at Aperture Opening (Selective Soldering)	Range: 70 to 140 °C
These are general guidelines which have proven to yield excellent results; however, depending upon your equipment, components, and circuit boards, your optimal settings may be different. To optimize your process, it is recommended to perform a design experiment, optimizing the most important variables (amount of flux applied, conveyor speed, topside preheat temperature, solder pot temperature and board orientation).	

Control: The foam applicators should be supplied with compressed air, free of oil and water. Maintain flux fluid level sufficiently above the aerator stone to produce adequate foam height. Adjust air pressure to produce the optimum height with foam consisting of small uniform bubbles.

During use, the acid number of the flux should be checked periodically. This can be accomplished using ALPHA Control Kit #3 or Titration Kit #9T for acid number monitoring. Evaporated solvent should be replenished by the addition of ALPHA 425 Flux Thinner to recover the nominal acid number of 18.0 mgKOH/gm. ALPHA FLS0016T-5D acid number control range during processing is 15 to 20 mgKOH/gm.

In time, debris and contaminants will accumulate in the flux. For consistent soldering performance, replace flux periodically. After dumping used flux, the reservoir and aerator stone should be thoroughly cleaned with flux thinner. Refill the reservoir with fresh flux and allow a few minutes for foam to stabilize before resuming solder operation.

Residue Removal: ALPHA FLS0016T-5D is a no-clean flux and the residues are designed to be left on the board. If desired, flux residues can be removed with ALPHA 2100 saponifier and aqueous cleaning equipment.

TECHNICAL DATA

Item	Typical Values	Item	Typical Values
Appearance	Clear, Colorless to Pale Yellow Liquid	Flash Point (T.C.C.)	12 °C
Solids Content, wt/wt	5%	Recommended Thinner	ALPHA 425
Specific Gravity @ 25 °C (77 °F)	0.809 ± 0.005	Shelf Life (from Date of Mfg.)	540 days
Acid Number (mg KOH/g)	18.0 ± 1.0	IPC J-STD-004 Designation	ORL0
pH, 5% aqueous	3.3		

CORROSION & ELECTRICAL RESISTANCE

CORROSION TEST

Test	Test Method	Results
Silver Chromate Paper	IPC-TM-650 2.3.33	PASS
Copper Mirror Test	IPC-TM-650 2.3.32	PASS
Copper Corrosion Test	JIS-Z-3197	PASS

SURFACE INSULATION RESISTANCE (all values in ohms)

Test	Requirement	Result
Comb Up	$> 1.0 \times 10^8$	4.3×10^9
Comb Down	$> 1.0 \times 10^8$	1.8×10^9
Test Condition (per IPC-TM-650 2.6.3.3): 85°C / 85%RH / 7 days		

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at MacdermidAlpha.com/assembly-solutions/knowledge-base.**

STORAGE

Store ALPHA FLS0016T-5D at 0 to 43 °C and prevent exposure to sunlight.

CONTACT INFORMATION

**To confirm this document is the most recent version, please contact
 Assembly@MacDermidAlpha.com
www.macdermidalpha.com**

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
---	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . . . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "®" and "™" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.