

# ALPHA<sup>®</sup> NR200

No-Clean / No Residue Flux

## DESCRIPTION

**ALPHA NR200** is a halide-free, rosin/resin free, low solids, no-clean flux for wave soldering through-hole, mixed technology and surface mount assemblies. It has a unique formulation that provides high activity with virtually no visible residue with most solder masks. ALPHA NR200 flux leaves a tack-free surface with high surface insulation resistance. **ALPHA NR200** features enhanced foam properties and low odor.

**ALPHA NR200** meets Bellcore specification TR-NWT-000078.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

## FEATURES & BENEFITS

Features	Benefits
Unique Low Solids Formulation	Eliminates the need for Cleaning
High Activity	Good Soldering; Low Defects
Halide Free	High Sir Values
No Visible Residue	Accurate Pin Testing and Enhanced Board Cosmetics
Enhanced Foaming Properties	Reduced Defects
Meets Bellcore Requirements	High Reliability Assemblies

**APPLICATION GUIDELINES**

ALPHA NR200 flux utilizes a unique blend of organic activators which significantly reduces solder bridging, icicing and solder balling on difficult to solder assemblies.

ALPHA NR200 flux can be applied by foam, by spray or by wave techniques. Topside preheat temperatures of 180 to 210 °F (80 to 100 °C) are recommended. Higher preheat temperatures can lead to premature volatilization of the activators, leading to less than optimal soldering performance. Best results are obtained using the following guidelines:

- a) Maintain a consistent foam head, spray volume or wave height.
- b) Replace the flux daily unless a sealed, self-contained system is available.
- c) Adjust the acid number as determined with the ALPHA Flux Solids Control Kit #3 to 18.0 (range +5, -2) with ALPHA 425 thinner.
- d) Add fresh ALPHA NR200 to maintain the appropriate flux level.
- e) Regularly clean the fluxing equipment. Equipment can be easily cleaned with sponge and water. For foam fluxers, the stone should be cleaned with ALPHA 425 thinner.

ALPHA NR200 flux can be maintained by monitoring specific gravity, but control by acid number determination is recommended.

**TECHNICAL DATA**

Item	Typical Values	Item	Typical Values
Appearance	Clear Colorless Liquid	Recommended Thinner	ALPHA 425
Solids Content, % wt/wt	2.0	Self-Life (from date of mfg.)	540 Days
Specific Gravity @ 25 °C (77 °F)	0.805 ± 0.003	IPC J-STD-004 Designation	ORM0
Acid Number (mg KOH/g)	18.0 ± 1.0	Package Size	1, 5 & 55 Gallons
Flash Point (T.C.C)	58 °F (14 °C)		

**CORROSION & ELECTRICAL TESTING**
**Corrosion Testing**

Test		Requirements for M0	Results
IPC	Silver Chromate Paper IPC-TM 650 Test Method 2.3.33	No detection of halide	PASS
	Copper Mirror Test IPC-TM 650 Test Method 2.3.32	<50% Breakthrough in test area	PASS

**J-STD-004A Surface Insulation Resistance**

Test	Conditions	Requirement	Results
“Comb-Down” Un-cleaned	85 °C/85% RH, 7 days	$>1.0 \times 10^8 \Omega$	$2.6 \times 10^9 \Omega$
“Comb-Up” Un-cleaned”	85 °C/85% RH, 7 days	$>1.0 \times 10^8 \Omega$	$5.0 \times 10^9 \Omega$
Control Boards	85 °C/85% RH, 7 days	$>1.0 \times 10^8 \Omega$	$7.3 \times 10^9 \Omega$

IPC Test Condition (per J-STD-004A): -50V, measurement @ 100V/IPC B-24 board (0.4 mm lines, 0.5 mm spacing).

**Bellcore Surface Insulation Resistance**

Test	Conditions	Requirement	Results
“Comb-Down” Un-cleaned	35 °C/85% RH, 5 days	$>1.0 \times 10^{11} \Omega$	$3.4 \times 10^{11} \Omega$
“Comb-Up” Un-cleaned”	35 °C/85% RH, 5 days	$>1.0 \times 10^{11} \Omega$	$6.3 \times 10^{12} \Omega$
Control Boards	35 °C/85% RH, 5 days	$>2.0 \times 10^{11} \Omega$	$2.2 \times 10^{12} \Omega$

Bellcore Test Condition (per GR 78-CORE, Issue 1): 48 Volts, measurement @ 100V/25 mil lines/50 mil spacing.

**Bellcore Electromigration**

Test	SIR (Initial)	SIR (Final)	Requirement	Result	Visual Result
“Comb-Down” Un-cleaned	$1.9 \times 10^{10} \Omega$	$1.9 \times 10^{10} \Omega$	SIR (Initial) / SIR (Final) <10	PASS	PASS
“Comb-Up” Un-cleaned”	$1.8 \times 10^{10} \Omega$	$1.9 \times 10^{10} \Omega$	SIR (Initial) / SIR (Final) <10	PASS	PASS

Bellcore Test Condition (per TR-NWT-000078 Issue 3): 85 °C/85% RH/500 Hours/10V, measurement @ 100V/IPC B-25B Pattern (12.5 mil lines, 12.5 mil spacing).

**RECYCLING SERVICES**

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



**SAFETY & WARNING**

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at [MacdermidAlpha.com/assembly-solutions/knowledge-base](http://MacdermidAlpha.com/assembly-solutions/knowledge-base).**

**CONTACT INFORMATION**

**To confirm this document is the most recent version, please contact  
 Assembly@MacDermidAlpha.com  
[www.macdermidalpha.com](http://www.macdermidalpha.com)**

<p><b>North America</b>                  109 Corporate Blvd.                  South Plainfield, NJ 07080, USA                  1.800.367.5460</p>	<p><b>Europe</b>                  Unit 2, Genesis Business Park                  Albert Drive                  Woking, Surrey, GU21 5RW, UK                  44.01483.758400</p>	<p><b>Asia</b>                  8/F., Paul Y. Centre                  51 Hung To Road                  Kwun Tong, Kowloon, Hong Kong                  852.3190.3100</p>
---	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.