

ALPHA[®] NR300

VOC-Free, No-Clean, No Residue Flux

DESCRIPTION

ALPHA NR300 is an essentially VOC-free, halide-free, rosin/resin free, low solids, no-clean flux. It is formulated for wave soldering of through-hole, mixed technology and surface mount assemblies. The flux produces a tack-free surface with high surface insulation resistance and no residue to interfere with electrical testing. It has a unique formulation that provides high activity with virtually no visible residue with most solder masks. **ALPHA NR300** conforms to the requirements of Bellcore TR-NWT-000078 for non-VOC flux formulations.

ALPHA NR300 flux is supplied in a water-based vehicle, free of organic solvents and is formulated to help meet the present and future volatile organic compound (VOC) emission regulations. The water vehicle results in a non-flammable product which does not require special storage conditions. A further unique property of the **ALPHA NR300** formulation is its ability to keep the organic activator system in solution after being submitted to storage temperatures below freezing.

ALPHA NR300 flux uses a unique blend of organic activators which significantly reduces solder bridging, icicling and solder balling on difficult to solder assemblies.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

Features	Benefits
VOC-free	Helps meet air quality regulations
Non-flammable	Eliminates equipment fires & eliminates special storing requirements
High activity	Good soldering; low defects
No thinners required	Reduced operating costs & less frequent solids analysis required
Meets Bellcore requirements	High reliability assemblies
No visible residue	Accurate pin testing & enhanced board cosmetics

APPLICATION GUIDELINES

ALPHA NR300 flux is engineered for spray applications only. Topside preheat temperatures of 104 to 116 °C (220 to 240 °F) are recommended. The optimum preheating settings and conveyor speed required to completely evaporate the water vehicle will be dependent upon the particular wave solder machine being used and the assemblies being processed. Insufficient preheat will be evident by spattering during wave soldering.

ALPHA NR300 flux, unlike conventional fluxes, does not require frequent thinning. Flux solids can be monitored using Alpha's Flux Solids Control Kit #3. If thinning is required, the addition of deionized water is all that is necessary.

For applications which specify cleaning, a plain heated water cleaning step after soldering will remove any slight traces of flux residues.

TECHNICAL DATA

Item	Typical Values	Item	Typical Values
Appearance	Clear, colorless liquid	Flash Point (T.C.C.)	N/A
Solids Content, %wt/wt	2.1	Recommended Thinner	DI Water
Specific Gravity @ 25 °C (77 °F)	1.006 ± 0.005	Shelf Life (from Date of Mfg.)	540 Days
Acid Number (mg KOH/g)	18.0 ± 1.0	IPC J-STD-004 Designation	ORL0
Halides	None	Packaging Size	25 Liters

CORROSION & ELECTRICAL TESTING
Corrosion Test

Test		Requirement	Results
IPC	Silver Chromate Paper (IPC-TM 650 Test Method 2.3.33)	No detection of halide	PASS
	Copper Mirror Test ¹ (Modified IPC/Bellcore Method)	No complete removal of copper	PASS

¹ Passes the copper mirror test when the same flux formulation is prepared using isopropyl alcohol instead of water. Also passes the copper mirror test when the same flux formulation is reconstituted with isopropyl alcohol after evaporation of its water vehicle at 85 °C.

Surface Insulation Resistance

Test	Conditions	Requirements	Results
IPC-SF-818, Class 3	85 °C/85% RH, 7 days	1.0 X 10 ⁸ Ω min.	1.2 X 10 ¹⁰ Ω
Bellcore-TR-NWT-000078, Issue 3: (4 days with bias voltage)			
"Comb-Up" Un-cleaned	35 °C/85% RH, 5 days	1.0 X 10 ¹¹ Ω min.	5.0 X 10 ¹² Ω
"Comb-Down" Un-cleaned	35 °C/85% RH, 5 days	1.0 X 10 ¹¹ Ω min.	1.3 X 10 ¹² Ω
Control Boards	35 °C/85% RH, 5 days	2.0 X 10 ¹¹ Ω min.	1.7 X 10 ¹² Ω

Electromigration Resistance

Test	SIR (Initial)	SIR (Final)	Requirement	Visual Result
"Comb-Up" Pattern	1.4 X 10 ⁹ Ω	2.1 X 10 ⁹ Ω	SIR(final)>(SIR(initial)/10)	No dendrites or corrosion
"Comb-Down" Pattern	7.0 X 10 ⁹ Ω	1.2 X 10 ⁹ Ω	SIR(final)>(SIR(initial)/10)	No dendrites or corrosion
Test Condition: Bellcore TR-NWT-000078, Issue 3, 85 °C/85% RH (500 Hrs. with 10 V bias)				

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at MacdermidAlpha.com/assembly-solutions/knowledge-base.**

STORAGE

Do not allow material to freeze. Material should be stored at 10 to 25 °C.

CONTACT INFORMATION

**To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com
www.macdermidalpha.com**

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. **READ IT THOROUGHLY PRIOR TO PRODUCT USE**. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. **NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE.** The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. “(R)” and “TM” are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.