

# ALPHA<sup>®</sup> RS7MI

## No Clean Cored Solder Wire

### DESCRIPTION

**ALPHA RS7MI** has an activated rosin flux core. The halide activator system provides extremely good tarnish removing properties. **ALPHA RS7MI** has good soldering performance even on very difficult soldering surfaces

**ALPHA RS7MI** leaves post-soldering residues that are hard and which can be safely left without need to remove them (depending on classification of end use product). If the removal of residues is required then, semi-aqueous or aqueous systems can be used effectively.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

### FEATURES & BENEFITS

Features	Benefits
Very fast wetting	Low Cycle times
Good spread characteristics	Excellent Solder Joints
Pleasant pine smell	Operator Friendly
Clear and safe residue	No-Clean Residues, Useful for all Applications
Provides good joint appearance	Makes Inspection easy

ALPHA RS7MI is suitable for use in any commercial no-clean hand soldering application that specifies compliance to J-STD-004 – ROM1.

It is suited to areas of industry that require higher flux activity levels to solder poor / highly tarnished surfaces, while still providing good reliability.

**PRODUCT INFORMATION**

Standard	Alloy Designation	Melting or Solidus / Liquidus Temp °C	Flux Amount
J-STD-006C	SAC305	217 to 221	2.2%
Proprietary	SACX Plus® 0307	217 to 228	2.2% & 3.3%
ISO9453	Sn97/Cu3	227 to 310	1.4% & 2.2%
ISO9453	Sn5/Pb93.5/Ag1.5	296 to 301	2.2%

\* ALPHA RS7MI may also be available in other or special alloys and flux amounts on request.

**APPLICATION GUIDELINES**

A soldered joint is formed by heating the parts to be soldered to a temperature in excess of the melting point of the alloy to be used – in hand soldering this is how a soldering iron is used. By feeding the cored wire onto the parts, the flux is able to flow and remove oxidized metal, while the solder creates a thin inter-metallic bond which becomes the solder joint.

ALPHA RS7MI is also ideal for robotic soldering applications. High quality spooling and precise wire diameters enable high productivity.

Note the following tips:

- Use a soldering iron tip size and form to suit the operation: small tips for soldering large components may prevent the formation of a joint or slow the process down.
- Select a solder wire diameter to suit both the soldering iron tip and the parts/components to be soldered.
- Soldering iron systems should provide sufficient heat to satisfy the requirements of the points above.
- Cored solder wires can be provided in different grades of alloy so always ensures that you have selected the right grade for the application.
- Do not overheat as this causes an increase in the depth of the inter-metallic layer, which in turn weakens the joint.

If you choose to use a liquid rework flux, ALPHA 615 Flux is recommended to maintain high electrical reliability. ALPHA 615 flux is available in ALPHA's 'Write Flux Pens' for precision flux application.

**TECHNICAL DATA**

Physical Properties	Typical Values
Rosin Softening Point:	72 °C (162 °F)
Acid Value:	175 to 195 mg KOH/g flux (IPC-TM-650-2.3.13)
Halide Content:	1.45 to 1.80% weight (IPC-TM-650-2.3.28.1)
Copper mirror:	<50% breakthrough per IPC J-STD-004
Classification:	ROM1 per IPC J-STD-004 ISO 12224 – 1.1.2. Din 8511 – F – SW26

Electrical Reliability Test	Requirements	Results
IPC SIR Testing (J-STD-004A)	1.0 × 10 <sup>8</sup> Ω minimum	PASS

**RECYCLING SERVICES**

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



**SAFETY & WARNING**

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at [MacDermidAlpha.com/assembly-solutions/knowledge-base](https://MacDermidAlpha.com/assembly-solutions/knowledge-base).**

**STORAGE**

ALPHA Cored Solder Wires should be stored in dry conditions and within a temperature range of 0 to 40 °C. Alpha guarantees the product shelf life for three years from the date of manufacture when stored in the recommended conditions.

**CONTACT INFORMATION**

**To confirm this document is the most recent version, please contact [Assembly@MacDermidAlpha.com](mailto:Assembly@MacDermidAlpha.com)**

[www.macdermidalpha.com](http://www.macdermidalpha.com)

<p><b>North America</b> 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460</p>	<p><b>Europe</b> Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p><b>Asia</b> 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.