

ALPHA[®] WS-619 Solder Paste

Water-Soluble; ORHO Per IPC-J-STD-004

DESCRIPTION

ALPHA WS-619 is completely water soluble, halide free solder paste. **ALPHA WS-619** is designed for stencil application in surface mounting processes where aqueous post reflow cleaning is required.

FEATURES & BENEFITS

- Shiny joints can be expected under a wide range of process conditions.
- Minimal foam is generated from cleaned flux residues in recirculating post-cleaning equipment.
- High Reflow Tolerance using a variety of reflow profiles & a wide temperature range.
- Excellent wetting characteristics on all types of copper protective coatings (including OSPs).
- Fast, accurate fine-pitch printing.

PRODUCT INFORMATION

<u>Alloys:</u>	63Sn/37Pb, 62Sn/36Pb/2Ag, SAC305
<u>Powder Size:</u>	Type 3, Type 4
<u>Packaging Sizes:</u>	500 gram jars, 6in & 12in cartridges, and 10cc & 30cc dispense syringes.
<u>FluxGel:</u>	ALPHA WS-619 Flux Gel is available in 10cc and 30cc syringes for rework applications.

APPLICATIONS GUIDELINES

Formulated for standard and fine pitch printing through stencil apertures as small as 0.008 inches (0.2 mm). Crisp, well defined print definitions are repeatably attainable on 0.016 inch (0.4mm) pitch pads.

TECHNICAL DATA

Category	Results	Procedures/Remarks
Fluxing Ability	Reflowed Solder Paste, Hot Solder Dip, Tin Plate, Tin Hot Dip, Silver Plate, Copper, Gold, Ag/Pd Plate, Cu Protective Coatings	Fluxing ability on tarnished surfaces
Chemical Properties		
Flux Designation	ORH0 – Organic Flux, High Activity, 0% Halide by titration	IPC J-STD-004
Electrical Properties		
SIR (IPC)	Pass ($>.10^8$ ohms), cleaned	4 day, 7 day 85 °C/85% RH
SIR (Bellcore)	Pass ($>10^{11}$ ohms), cleaned	4 days, 35 °C/85% RH
Electromigration (500 hour Bellcore)	Pass visual and electrical, cleaned	500 hrs, 85 °C/85% RH
Color	Clear, Colorless Flux Residue	
Tack Force	$> 1.5 \text{ g/mm}^2$ @ 6 hours	J-STD-005, See figure #2
Stencil Life	> 4 hours	@ 50%RH, 72 °F
Slump	Suitable for fine pitch printing applications	IPC TM-650

PROCESSING GUIDELINES

The following is a review of general application notes and precautions.

Storage-Handling	Printing	Reflow (See Figure 1a and 1b)	Cleaning
<ul style="list-style-type: none"> Refrigerate to guarantee stability @ 32 to 50 °F (0 to 10 °C) Shelf life of refrigerated paste is three months. Warm-up 500g jar to room temperature (should be ~ 4 hours). Set up printer with room temperature paste. Check paste temperature with a thermometer. Do not remove worked paste from stencil and mix with unused paste in jar. This will alter rheology of unused paste. 	<p>Stencil: Recommend Alpha laser cut stencil @ 0.006 inch thick for 0.020 mil pitch (.008 inch thick for 0.025 inch pitch) or Alpha manufactured chemically etched stencil.</p> <p>Squeegee: Recommend metal or 90 durometer polyurethane.</p> <p>Pressure: 1 to 2.0 pounds per linear inch of print pattern.</p> <p>Speed: 0.5 to 4.0 inch (15 to 150mm) per second</p> <p>Paste Roll: 0.4 to 0.6 inches (1 to 1.5 cm) diameter and make additions when roll reaches 0.2 inch (0.5cm) diameter.</p>	<ul style="list-style-type: none"> Use convection, IR, or combination ovens, hot -plate, vapor phase. Clean-dry air or nitrogen atmosphere. <p>PROFILE (63/37 Alloy): The following profile is provided as an initial guide to reflow of ALPHA WS-619. Changes may be required on differences in thermal inertia and component sensitivity.</p> <ul style="list-style-type: none"> Ramp @ 60 to 120 °C /min. to 125 to 160 °C. Dwell @ 125 to 160 °C for 0.5 to 2.0 minutes. Ramp @ 60 to 120 °C /min to 210 to 225 °C peak temp. Time over 183 °C = 45 to 75 sec Ramp down to R.T. @ 90 to 120 °C/min. Ensure solder is frozen at exit of last heated zone to avoid disturbed joint defects. <p>SAC305 Profile</p> <ul style="list-style-type: none"> Ramp @ 1.0 to 2.0 °C /sec. to 130 °C. Slow ramp from 130 °C for 90 to 120 seconds Ramp @ 0.5 to 2 °C/sec to peak temperature 230 to 250 °C TAL for 40 to 80 seconds. Ramp down to R.T @ 1 to 3 °C/sec. 	<p>ALPHA WS-619 is designed to be water rinsed in washing operations with minimal foaming in recirculating systems.</p> <p>The flux residues from ALPHA WS-619 are completely water soluble. Suggestions for optimized cleaning: Wash within 24 hours of reflow. 2 hours for best performance.</p> <p>Use deionized water 120 to 140° F wash and rinse temperatures.</p> <p>Allow assemblies to first cool to below wash temperature.</p> <p>Low pressure/high water volume washing.</p> <p>High volume/low temperature drying.</p> <p>Perform regular filter maintenance in recirculating systems.</p>

REFLOW PROFILES

Figure 1a: SAC305 Reflow Profile




Figure 1b: Tin/Lead Reflow Profile





Figure 2: Tack vs. Time



BIOACT is a registered trademark of Petroferm, Inc. EC-7, EC-7R and EC-8 are trademarks of Petroferm, Inc.

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at MacDermidAlpha.com/assembly-solutions/knowledge-base.**

STORAGE

ALPHA WS-619 is shipped in thermally controlled boxes and should be stored refrigerated upon receipt at 32 to 50 °F (0 to 10 °C). This will be sufficient to maintain a nominal shelf life of 3 months. ALPHA WS-619 should be permitted to reach room temperature before unsealing its package prior to use.

CONTACT INFORMATION

**To confirm this document is the most recent version, please contact
Assembly@MacDermidAlpha.com**

www.macdermidalpha.com

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
---	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.