

STAYSTIK® 336T

Non-Filled Dielectric Wafer Coat

DESCRIPTION

STAYSTIK® 336T is a thermoplastic polymer specially developed as a temporary bonding adhesive for GaN, GaAs, SiC, and Si wafer thinning in the semiconductor industry. It can also be used for a variety of applications where temporary adhesion is necessary. This adhesive can be easily debonded with Isopropyl Alcohol (I.P.A.)/Acetone leaving no residue or contamination on the surface of the debonded assembly.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

KEY FEATURES & BENEFITS

- Excellent wetting
- Easy removal at elevated temperatures
- Excellent solubility with a variety of solvents, easy cleaning process
- No residue or contamination after cleaning

APPLICATIONS

- * Wafer Lapping
- * Substrate Cutting
- * Wafer Cutting
- * Wafer Polishing
- * Row Bonding for Dicing
- * Lens Polishing

PROCESSING GUIDELINES (Unfilled Paste)

Spin Coating and Hot Plate Baking Processes

Wafer	Hot Plate Bake Temperature (°C)	Spin (krpm)	Time (sec)	Approx. Coating Thickness (µm)
SiC	90	1.3	30	16-17
GaAs/Si	125			
Si	125	1.5		23

- Attach or bonding temperature: 150-160°C
- Wafer debonding or demount temperature: >200°C

- Clean up and removal: Immerse the bonded materials in Isopropyl Alcohol, Acetone, or NMP and allow sufficient immersion time for material to dissolve the adhesive under bonded material

TYPICAL PROPERTIES

Material Properties (Undried)	Method	Value	Remarks
Chemical type		Acrylic Thermoplastic	
Color	Visual	Clear/Amber	
Specific gravity	ASTM D792-00	0.89 g/cm ³	
Dynamic Viscosity @ 1rpm	ASTM D2196-99	2400 mPa·s	@25°C
Dynamic Viscosity @ 10rpm	ASTM D2196-99	2000 mPa·s	@25°C
Flashpoint	ASTM D-93-02	32°C	Tag Closed Cup
Filler Content		0%	
Storage Temperature (Metal Cans)		25°C	
Storage Temperature (Plastic Syringes)		0-10 (°C)	
Shelf Life @ Storage Temperature		12 months	

CLEAN-UP

Undried material may be cleaned from dispenser components and surfaces with a variety of solvents, including IPA, acetone, NMP, MEK, methylene chloride, etc. Always wash and dry thoroughly prior to reuse of the dispenser components. The cleaning technique should be active cleaning of the components – flush, wash or wipe, followed by a drying step to ensure a clean, dry surface. Contact your equipment supplier to ensure the solvent is compatible with their components. Clean and maintain dispense valves as recommended by the equipment manufacturer.

PACKAGING SIZES

This product is available in (250g, 500g) metal cans and (3, 5, 10, 30 or 55) cc cartridges that are compatible with both time/pressure and positive displacement dispense systems.

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available..**

WASTE TREATMENT

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedent.

CONTACT INFORMATION

To confirm this document is the most recent version, please contact
techinfo@MacDermidAlpha.com
www.macdermidalpha.com

North America 3950 Johns Creek Ct, Suite 300 Suwanee, GA 30024 USA 908.791.2300	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 14 Joo Koon Crescent, Singapore 629014 65.6430.0700
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.