

# ATROX® CF.200-1D

## High Thermal Conductive Die-attach Film

### DESCRIPTION

ATROX® CF200-1D is a conductive film adhesive with high electrical and thermal conductive properties. The unique chemistry allows excellent process flexibility and superior reliability performance to a variety of die sizes used for semiconductor applications. The film has excellent adhesion to Silicon wafers as well metallized dies and commonly used lead-frame surface finishes such as Bare Cu, Ag and NiPdAu.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

### KEY FEATURES & BENEFITS

- High thermal and electrical conductivity
- Excellent adhesion and low modulus allow for superior delamination resistance to most lead-frame surfaces
- No Resin bleed out
- Consistent Bond Line Thickness control
- Low ionic content.

### TYPICAL PROPERTIES

Film Properties	Test Method	Value
VR	4-Point Probe	0.00007 ohm-cm
Thermal Conductivity	Laser-Flash	20 W/m-K
Modulus 25°C	DMA	6.6 GPa
Modulus 250°C	DMA	0.84 GPa
Tg	TMA	97 °C
CTE-1	TMA	53 ppm
CTE-2	TMA	162 ppm
Weight loss during cure	TGA	0.4%
Conductive Film Thickness		15µm

Film Properties	Test Method	Value
Shelf Life (@ 0°C)		6 months
Work life after Thawing/Lamination*	25°C Storage	1 month

\*Wafer Lamination should be carried out as soon as films have been thawed

\*\*Dicing Tape details are available in TDS of Dicing Tape NU30-2


## PROCESS RECOMMENDATIONS

Process	Parameters
Wafer lamination temperature	75 to 85 °C
Die attach condition	130 to 150 °C/1-30N/0.5-2sec (Depending on die size)
Cure condition	45min ramp to 200C + hold at 200C for 90min Alternate cure profile for enhanced adhesion: 60 min to 250C + Hold at 250C for 90 minutes

## MATERIAL APPLICATION

The Conductive film typically requires pressure during die bonding to ensure wetting of Lead-frame surfaces. The pressure will be dependent upon die size and thickness. It is critical that lead-frames reach the required temperature. Pressure should be around 10-30N during die attach. Bonding surfaces should be clean and free from oils, dust, etc as these can interfere with adhesion and thermal/electrical properties.

## CURE



## PACKAGING SIZES

ATROX® CF200-1D is available in pre-cut format roll of varying lengths for different wafer sizes. Standard thickness is 15 µm

### SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

### SHIPPING & STORAGE

Material should be stored at 0°C for a maximum shelf life of 6 months or alternatively for 1 month at room temperature. It is recommended that the material be allowed to reach room temperature before opening and handling. Remove the film form storage, allowing it to come to room temperature, before usage.

### CONTACT INFORMATION

To confirm this document is the most recent version, please contact  
[techinfo@MacDermidAlpha.com](mailto:techinfo@MacDermidAlpha.com)

[www.macdermidalpha.com](http://www.macdermidalpha.com)

<b>North America</b> 3950 Johns Creek Ct, Suite 300 Suwanee, GA 30024 USA 908.791.2300	<b>Europe</b> Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	<b>Asia</b> 14 Joo Koon Crescent, Singapore 629014 65.6430.0700
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "®" and "™" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.