

ALPHA[®] RMA-390 DH3 SOLDER PASTE

DESCRIPTION

ALPHA RMA-390 DH3 is a rosin based solder paste designed for surface mount and other demanding electronic assembly applications. The rosin base flux has been shown to withstand temperatures in excess of 300 °C and capable in high lead or lead-free alloy compositions.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PRODUCT INFORMATION

ALPHA RMA-390 DH3 is available in the following Vaculoy alloys:

Alloys: 62Sn/36Pb/2Ag, 63Sn/37Pb, 96.5Sn/3.5Ag, 10Sn/88Pb/2Ag, SAC305, 5Sn/92.5Pb/2.5Ag

Powder Size: Type 2, Type 3, Type 4

Packaging Sizes: 500 gram jars, 6in & 12in cartridges, 10 and 30 cc syringes

TECHNICAL DATA

Property	Result	Procedure
Chemical Properties		
Activity level	ROL1 J-STD classification, Cu mirror corrosivity – PASS (L)	IPC J-STD 004
	Cu corrosion (10 day) – PASS	IPC J-STD 004
Halide Content	< 0.05 %	Titration
Electrical Properties		
SIR (7 days 85 °C / 85 %RH)	2.8 x 10 ⁹ Ohms (Pass > 1 x 10 ⁸)	IPC J-STD 004
SIR (Bellcore 96 hrs, 35 °C/85% RH)	4.6 x 10 ¹¹ Ohms (Pass > 1 x 10 ¹¹)	Bellcore GR78-CORE
Electromigration (Bellcore 500 hrs 65 °C/85%RH)	Initial: 1.52 x 10 ⁹ Ohms Final: 5.68 x 10 ⁹ Ohms	Bellcore GR78-CORE (Pass: Final > Initial / 10)

Additional Designation (per obsolete specification): RMA, meets QQS-S-571E, Q.P.L listed #57102086

APPLICATION GUIDELINES

ALPHA RMA-390 DH3 can be applied by stencil or by screen. Working time on the stencil or screen is about four (4) hours. Tack time is about four (4) hours. This product is extremely versatile and can be accommodated to a wide variety of specifications.

The production environment should be 19 to 27 °C (65 to 80 °F) and 30 to 60% RH.

REFLOW PROFILES

Reflow (Sn/Pb Alloys)

Reflow of ALPHA RMA-390DH3 can be achieved with a variety of equipment including Infrared, Convection, Vapor Phase, Conductive Belt, or Hot Air. Since substrates and components come to thermal equilibrium based on surface area and mass, the following describe equilibrium temperatures measured at board level. A representative IR profile is given below.

Reflow	Recommendation
Ramp Rate	1 to 3 °C/sec. to 120 to 160 °C
Soak	120 to 160 °C for 2 minutes
Ramp Rate	0.5 to 1 °C/second to 210 to 230 °C
Time Above Liquidus	45 to 75 seconds

Alloy	Liquidus °C (°F)	Solidus °C (°F)
62Sn/36Pb/2Ag	179 (354)	179 (354)
63Sn/37Pb	183 (361)	183 (361)
96.5Sn/3.5Ag	221 (430)	221 (430)
10Sn/88Pb/2Ag	299 (570)	268 (514)
5Sn/92.5Pb/2.5Ag	296 (565)	287 (549)

Total heating dwell time may be 4 to 7 min. depending on thermal inertia and component sensitivity.

Reflow SAC305 Alloy

Setting Zone*	Optimal Dwell Period	Extended window
40 to 221 °C	2:30 to 4:30 min.	< 5:00 min.
170 to 221 °C	0:30 to 2:00 min	< 2:30 min.
120 to 221 °C	1:25 to 3:00 min.	< 3:30 min.
TAL (217 to 221 °C)	45 to 90 sec.	Not Recommended
Peak temperature	235 to 245 °C	Compatible with most common surface finishes. (ENTEK HT, ENTEK OM, AlphaSTAR, ENIG, SACX® HASL). Coldest point on the PCB can be as low as 230 °C. Paste can withstand 250 °C during reflow.
Joint cool down rate	-1 to -6 °C/second	Recommended to prevent surface cracking issues.

Alloy	Meting Range
SAC305	217 to 221° Melting Range

SHIPPING

Temperatures over 32 °C (90 °F) should be avoided in handling ALPHA RMA-390 DH3. During the summer, this product is shipped in a thermally controlled carton. It should not be left on a shipping dock or exposed to heat after receipt.

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at MacdermidAlpha.com/assembly-solutions/knowledge-base.**

STORAGE

Refrigerated storage is required. Typically, paste should be stored at 0 to 10 °C (32 to 50 °F). Before use, paste should be allowed to come to room temperature. Shelf life of paste refrigerated at 0 to 10 °C (32 to 50 °F) is six months from date of manufacture.

CONTACT INFORMATION

**To confirm this document is the most recent version, please contact
 Assembly@MacDermidAlpha.com
www.macdermidalpha.com**

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
---	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. “(R)” and “TM” are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.